

Application No.: 10/608,026
Amendment dated September , 2005
Reply to Office Action of March 14, 2005

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1-11. (withdrawn from this election):

12 (Original): A radiation cross-linkable medical angioplasty balloon or radiation cross-linkable medical catheter made from a thermoplastic cross-linkable composition, said thermoplastic cross-linkable composition comprising: (a) a thermoplastic polymer selected from the group consisting of nylon, a copolyester copolymer of poly(1,4-butanediol terephthalate) and poly(alkylene ether terephthalate), a copoly(ether-ester-amide) polymer, and copolymers of polylaurinlactam and polytetrahydrofuran, and a reaction product of an aliphatic polyisocyanate and a polyah; and (b) a monomer cross-linker comprising acrylate monomer crosslinkers, said monomer cross-linker present in said composition in an amount sufficient to provide cross-linking of at least a portion of said thermoplastic polymer to convert said portion from a thermoplastic to a thermoset state upon irradiation of said composition with energy from a radiation source.

13 (Original): A radiation cross-linked medical angioplasty balloon or radiation cross-linked medical catheter made by irradiating the radiation crosslinkable medical angioplasty balloon of claim 12 with energy from a radiation source.

14 (Original): The radiation cross-linkable medical angioplasty balloon or radiation cross-linkable medical catheter of claim 12, wherein said thermoplastic polymer is a thermoplastic elastomer.

15 (Original): The radiation cross-linkable medical angioplasty or radiation cross-linkable medical catheter balloon of claim 12, wherein said thermoplastic polymer is a block copolymer containing hard and soft segments.

Application No.: 10/608,026
Amendment dated September , 2005
Reply to Office Action of March 14, 2005

16 (Original): The radiation crosslinked medical angioplasty balloon or radiation cross-linked medical catheter of claim 13, wherein said energy is in the form of free radical initiating or ionizing radiation selected from the group consisting of beta particles, gamma particles, ultraviolet radiation, electron beam radiation, and combinations thereof.

17 (Original): The radiation cross-linkable medical angioplasty balloon or radiation cross-linkable medical catheter of claim 12. wherein said monomer cross-linker is trimethylolpropane triacrylate.

18 (Original): A radiation cross-linked medical angioplasty balloon or radiation cross-linked medical catheter made from a cross-linked composition, wherein said cross-linked composition is produced by irradiating a crosslinkable composition comprising: (a) a thermoplastic polymer selected from the group consisting of nylon, a copolyester copolymer of poly(1,4-butanediol terephthalate) and poly(alkylene ether terephthalate), a copoly(ether-ester-amide) polymer, and copolymers of polylaurinlactam and polytetrahydrofuran, and a reaction product of an aliphatic polyisocyanate and a polyah; and (b) a monomer cross-linker comprising acrylate monomer crosslinkers, said monomer cross-linker present in said composition in an amount sufficient to cross-link at least a portion of said thermoplastic polymer to convert said portion from a thermoplastic to a thermoset state upon irradiation of said composition with energy from a radiation source.

19 (Original): The radiation cross-linked medical angioplasty balloon or radiation cross-linked medical catheter of claim 18, wherein said thermoplastic polymer is a thermoplastic elastomer.

20 (Original): The radiation cross-linked medical angioplasty balloon or radiation cross-linked medical catheter of claim 18, wherein said thermoplastic polymer is a block copolymer containing hard and soft segments.

Application No.: 10/608,026
Amendment dated September , 2005
Reply to Office Action of March 14, 2005

21 (Original): The radiation crosslinked medical angioplasty balloon or radiation cross-linked medical catheter of claim 18, which is produced by irradiating said cross-linkable composition with energy in the form of free radical initiating or ionizing radiation selected from the group consisting of beta particles, gamma particles, ultraviolet radiation, electron beam radiation, and combinations thereof.

22 (Original): The radiation cross-linked medical angioplasty balloon or radiation cross-linked medical catheter of claim 18, wherein said monomer cross-linker is trimethylolpropane triacrylate.

23. (currently amended): The radiation crosslinked composition made by irradiating the radiation crosslinkable composition comprising: (a) a thermoplastic copoly(ether-ester-amide) polymer and (b) a monomer cross-linker selected from the group consisting of triallylisocyanurate ("TAIC") or triallylcyanurate ("TAC") ~~allylic monomers~~, and combinations thereof, with energy from a radiation source, wherein said radiation crosslinked composition is in the form of a device selected from the group consisting of ~~surgical gloves, angioplasty balloons, birth control sheathes, heat shrinkable tubing, heat-shrinkable film, wire and cable jackets, orthodontic ligatures, seals, gaskets, and o-rings, shoe soles, toner wiper blades, medical implant devices, and coated wires.~~

24. (currently amended): A device selected from the group consisting of ~~surgical gloves, angioplasty balloons, birth control sheathes, heat shrinkable tubing, heat-shrinkable film, wire and cable jackets, orthodontic ligatures, seals, gaskets, and o-rings, shoe soles, toner wiper blades, medical implant devices, and coated wires~~ containing a radiation crosslinked composition made by irradiating ~~the~~ a radiation crosslinkable composition comprising: (a) a thermoplastic copoly(ether-ester-amide) polymer and (b) a monomer cross-linker selected from the group consisting of triallylisocyanurate ("TAIC") or triallylcyanurate ("TAC") ~~allylic monomers~~, and combinations thereof, with energy from a radiation source.

Application No.: 10/608,026
Amendment dated September , 2005
Reply to Office Action of March 14, 2005

25. (not in this election):

26. (currently amended): An article suitable for, sterilization by exposure to heat or, sterilization by exposure to radiation, surface modification by exposure to radiation or surface grafting by exposure to radiation, comprising a cross-linked composition, wherein said cross-linked composition is free of aromatic carbonyl compounds and is produced by irradiating a crosslinkable composition comprising: (a) a thermoplastic polymer selected from the group consisting of nylon, a copolyester copolymer of poly(1,4-butanediol terephthalate) and poly(alkylene ether terephthalate), a copoly(ether-ester-amide) polymer, and copolymers of polylaurinlactam and polytetrahydrofuran, and a reaction product of a polyisocyanate and a polyal; and combinations thereof, and (b) a monomer cross-linker selected from the group consisting of allylic monomer crosslinkers, methacrylate monomer crosslinkers, acrylate monomer crosslinkers, and combinations thereof; said monomer cross-linker present in said composition in an amount sufficient to cross-link at least a portion of said thermoplastic polymer to convert said portion from a thermoplastic to a thermoset state upon irradiation of said composition with energy from a radiation source, wherein the amount of crosslinked composition is sufficient to increase the radiation tolerance or heat sterilization tolerance of the article over that of the article alone without the crosslinked composition.

27 (Original): The article of claim 26, wherein said article is a medical device.

28 (Original): The article of claim 26, wherein said article has been subjected to radiation or heat in an amount sufficient to sterilize that article or wherein said article has been subjected to radiation in an amount sufficient to graft or modify the surface of that article.

29. (currently amended): An article suitable for, sterilization by exposure to heat or, sterilization by exposure to radiation, surface modification by exposure to radiation or

Application No.: 10/608,026
Amendment dated September , 2005
Reply to Office Action of March 14, 2005

surface grafting by exposure to radiation, comprising a cross-linkable composition,
wherein said cross-linkable

composition is free of aromatic carbonyl compounds and comprises: (a) a thermoplastic polymer selected from the group consisting of nylon, a copolyester copolymer of poly(1,4-butanediol terephthalate) and poly(alkylene ether terephthalate), a copoly(ether-ester-amide) polymer, and copolymers of polylaurinlactam and polytetrahydrofuran, and a reaction product of a polyisocyanate and a polyah; and combinations thereof, and (b) a monomer cross-linker selected from the group consisting of allylic monomer crosslinkers, methacrylate monomer crosslinkers, acrylate monomer crosslinkers, and combinations thereof; said monomer cross-linker present in said composition in an amount sufficient to provide cross-linking of at least a portion of said thermoplastic polymer from a thermoplastic to a thermoset state upon irradiation of said composition with energy from a radiation source, wherein the amount of crosslinkable composition is sufficient to increase the radiation sterilization tolerance of the article over that of the article alone without the crosslinkable composition.

30 (Original): The article of claim 29, wherein said article is a medical device.

31 (Original): The article of claim 29, wherein said article has been subjected to radiation in an amount sufficient to sterilize that article or wherein said article has been subjected to radiation in an amount sufficient to graft or modify the surface of that article.

32. (currently amended): An wholly or partially encapsulated device, wholly or partially encapsulated with a cross-linkable composition; ~~wherein said cross-linked composition is~~ produced by irradiating a crosslinkable composition comprising: (a) a thermoplastic polymer selected from the group consisting of nylon, a copolyester copolymer of poly(1,4-butanediol terephthalate) and poly(alkylene ether terephthalate), a copoly(ether-ester-amide) polymer, and copolymers of polylaurinlactam and polytetrahydrofuran, and a reaction product of a polyisocyanate and a polyah; and combinations thereof; and (b) a

Application No.: 10/608,026
Amendment dated September , 2005
Reply to Office Action of March 14, 2005

monomer cross-linker selected from the group consisting of allylic monomer crosslinkers, methacrylate monomer crosslinkers, acrylate monomer crosslinkers, and combinations thereof; with the proviso that for the reaction product of a polyisocyanate and a polyah the monomer acrylic or methacrylic cross-linker is other than trimethylolpropane triacrylate, trimethylolpropane trimethacrylate, and triacrylfomal, said monomer cross-linker present in said composition in an amount sufficient to provide cross-linking of at least a portion of said thermoplastic polymer from a thermoplastic to a thermoset state upon irradiation of said composition with energy from a radiation source, and wherein the crosslinked encapsulation composition is expanded to a larger size than the device to be encapsulated, by a heating and forming process, and then cooled to retain the expanded size, said expanded crosslinked encapsulation composition possessing the characteristic of "memory" due to the crosslinked polymer comprising the crosslinked encapsulation composition, and wherein the ~~medica~~ device to be wholly or partially encapsulated is placed within the expanded shaped object with "memory", and wherein heat is applied to cause the expanded crosslinked encapsulation composition with "memory" to contract and wholly or partially encapsulate the device within.

33 (Original): The device of claim 32, wherein said device is a medical device.